

AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Currently Amended) A gas-barrier laminate comprising
a plastic substrate (A),
an inorganic film (B) having a thickness of 0.5 to 40 nm formed on at least one surface of
the plastic substrate (A),
an anchor coat layer disposed between plastic substrate (A) and inorganic film layer (B),
and
a polyester-based resin layer (C) having a thickness of 0.5 to 5 μm formed by applying a
coating material containing a polyester-based resin on a surface of the inorganic film (B),
said polyester-based resin having a glass transition temperature of 50 to 70°C, a weight
average molecular weight of 1500 to 15000 and a hydroxyl value of 10 to 60 mg KOH/g, and
said gas-barrier laminate having an oxygen permeability of not more than 5
 $\text{cc}/\text{m}^2/\text{day}/\text{atm}$ and a water vapor permeability of not more than 5 $\text{g}/\text{m}^2/\text{day}$.

2. (Currently Amended) A gas-barrier laminate according to claim 1, wherein the plastic
substrate (A) comprises a polyester resin, a nylon resin, a polyolefin resin or a biodegradable
resin selected from starch/polycaprolactone, polycaprolactone, polyethylene succinate,
polybutylene succinate, polybutylene succinate/adipate, polyester carbonate, aromatic polyester,
cellulose acetate and chemically modified starch.

3. (Previously Presented) A gas-barrier laminate according to claim 1, wherein the coating material contains a fatty acid, a fatty ester, a fatty amide or a mixture thereof in an amount of 0.1 to 20 parts by weight based on 100 parts by weight of the polyester-based resin.

4. (Previously Presented) A gas-barrier laminate according to claim 1, wherein the coating material contains a polyisocyanate as a curing agent.

5. (Original) A gas-barrier laminate according to claim 4, wherein a content of the polyisocyanate in the coating material is 0.8 to 1.5 times a hydroxyl equivalent of the polyester-based resin.

6. (Canceled).

7. (Previously Presented) A gas-barrier laminate according to claim 1, wherein the inorganic thin film (B) is a physically vapor-deposited film or a chemically vapor-deposited film comprising silicon oxide, aluminum oxide, diamond-like carbon or a mixture thereof.

8. (Canceled).

9. (Currently Amended) A gas-barrier laminate according to claim ~~[[8]]~~1, wherein the anchor coat layer comprises at least one material selected from the group consisting of a polyester-based resin, an urethane resin, an acrylic resin and an oxazoline group-containing resin.

10. (Previously Presented) A gas-barrier laminate according to claim 1, further comprising a printed layer formed on a surface of the polyester-based resin layer (C), and a heat seal layer formed on a surface of the printed layer.

11. (Original) A gas-barrier laminate according to claim 10, further comprising at least one paper or plastic film disposed between the printed layer and the heat seal layer.

12. (Currently Amended) A gas-barrier laminate according to claim ~~[[8]]~~1, wherein after forming the inorganic film (B) on the plastic substrate (A) or on the anchor coat layer formed on the plastic substrate (A), the resultant laminate is heat-treated at a temperature of not less than 60°C, and then the coating material containing the polyester-based resin is applied onto the inorganic thin film (B) to form the polyester-based resin layer (C) thereon.

13. (Previously Presented) A gas-barrier laminate according to claim 1, wherein when the laminate is subjected to hydrothermal treatment under pressure at 120°C for 30 min, a ratio of an oxygen permeability of the laminate before the hydrothermal treatment to that after the hydrothermal treatment is not more than 5.

14. (Currently Amended) A gas-barrier laminate according to claim ~~[[8]]~~1, wherein when the laminate is subjected to hydrothermal treatment under pressure at 120°C for 30 min, an adhesion strength between the plastic substrate (A) or the anchor coat layer formed on the plastic substrate (A) and the inorganic film (B) is not less than 100 g/15 mm.

15. (Previously Presented) A gas-barrier laminate according to claim 1, wherein when the laminate is subjected to hydrothermal treatment under pressure at 120°C for 30 min, an adhesion strength between the printed layer and the polyester-based resin layer is not less than 100 g/15 mm.